

AGSORB[®]



24/48 RVM ^{tan} CA

TYPICAL PRODUCT DATA

Size Guide Number.....	55	TESTING METHOD	
Uniformity Index.....	40	PS 006.01.01 (GSA)	
Liquid Holding Capacity (% BY WEIGHT).....	27	PS 006.01.01 (GSA)	
Bulk Density (LBS/FT ³).....	39	E1521-93 (ASTM)	
pH.....	8	E727-91 (ASTM)	
Moisture Content (% BY WEIGHT).....	<6	D2216-80 (ODC)	
Particle Count (MM/LB).....	5	E1520-93 (ASTM)	
Attrition (% RESISTANCE).....	75-85	P-A 1056 B (GSA)	

PRODUCT DESCRIPTION

This fine sized granule has a high particle count for excellent coverage of treatment areas. Its characteristics make it well suited as a carrier in crop protection and turf/ornamental applications. This RVM material, though not calcined, exhibits similar attrition properties to LVM minerals.

MINERAL DESCRIPTION

AGSORB[®] from Taft, California is a Hydrous Aluminosilicate mineral. Its low bulk density and high absorptivity allows higher liquid holding capacity. Our mineral processing maximizes the granule's micropore space. AGSORB[®] heat treatments impart a hard, inert granule with a high resistance to attrition. The unique properties of this mineral make it harder in its natural state than other RVM products.

TYPICAL CHEMICAL ANALYSIS

Component	Weight %
VOLATILE FREE BASIS	
SiO ₂	80.0
Al ₂ O ₃	9.0
Fe ₂ O ₃	1.0
Other Salts.....	2.0
H ₂ O.....	8.0



TAFT, CALIFORNIA