

AGSORB®



5/20 RVM ^{tan} CA

TYPICAL PRODUCT DATA

Size Guide Number.....	215	TESTING METHOD	
Uniformity Index.....	25	PS 006.01.01 (GSA)	
Liquid Holding Capacity (% BY WEIGHT).....	27	PS 006.01.01 (GSA)	
Bulk Density (LBS/FT ³).....	40	E1521-93 (ASTM)	
pH.....	8	E727-91 (ASTM)	
Moisture Content (% BY WEIGHT).....	<5	D2216-80 (ODC)	
Particle Count (MM/LB).....	0.4	E1520-93 (ASTM)	
Attrition (% RESISTANCE).....	75-85	P-A 1056 B (GSA)	

PRODUCT DESCRIPTION

This coarse sized granule is frequently used as a fertilizer conditioner or drying agent for agricultural grade and turf/ornamental applications. Commonly used as a component in growing media. This RVM material, though not calcined, exhibits similar attrition properties to LVM minerals.

MINERAL DESCRIPTION

AGSORB® from Taft, California is a Hydrous Aluminosilicate mineral. Its low bulk density and high absorptivity allows higher liquid holding capacity. Our mineral processing maximizes the granule's micropore space. AGSORB® heat treatments impart a hard, inert granule with a high resistance to attrition. The unique properties of this mineral make it harder in its natural state than other RVM products.

TYPICAL CHEMICAL ANALYSIS

Component	Weight %
VOLATILE FREE BASIS	
SiO ₂	80.0
Al ₂ O ₃	9.0
Fe ₂ O ₃	1.0
Other Salts.....	2.0
H ₂ O.....	8.0



TAFT, CALIFORNIA