

AGSORB®



24/48 RVM ^{tan} GA

TYPICAL PRODUCT DATA

Size Guide Number.....	55	TESTING METHOD	
Uniformity Index.....	40	PS 006.01.01 (GSA)	
Liquid Holding Capacity (% BY WEIGHT).....	32	PS 006.01.01 (GSA)	
Bulk Density (LBS/FT ³).....	33	E1521-93 (ASTM)	
pH.....	7	E727-91 (ASTM)	
Moisture Content (% BY WEIGHT).....	10	D2216-80 (ODC)	
Particle Count (MM/LB).....	8.8	E1520-93 (ASTM)	
Attrition (% RESISTANCE).....	75-85	P-A 1056 B (GSA)	

PRODUCT DESCRIPTION

This fine sized granule has a high particle count for excellent coverage of treatment areas. Its characteristics make it well suited as a carrier in crop protection and turf/ornamental applications. This RVM material will revert to its colloidal state (slake) in some applications.

MINERAL DESCRIPTION

AGSORB® from Ochlocknee, Georgia is an Attapulgite mineral in the non-swelling bentonite class. It is commonly called Fuller's earth. Its low bulk density and high absorptivity allows higher liquid holding capacity. Our mineral processing maximizes the granule's micropore space. AGSORB® heat treatments impart a hard, inert granule with a high resistance to attrition.



**OCHLOCKNEE,
GEORGIA**

TYPICAL CHEMICAL ANALYSIS

Component	Weight % VOLATILE FREE BASIS
SiO ₂	70.81
Al ₂ O ₃	14.12
CaO.....	2.22
MgO.....	4.57
Na ₂ O.....	0.23
K ₂ O.....	1.30
Fe ₂ O ₃	4.98
MnO.....	0.04
P ₂ O ₅	0.99
TiO ₂	0.62
FeO.....	0.11
Loss on Ignition.....	6.0