

AGSORB®



5/20 LVM ^{gray} IL

TYPICAL PRODUCT DATA

Size Guide Number.....	215
Uniformity Index.....	35
Liquid Holding Capacity (% BY WEIGHT).....	30
Bulk Density (LBS/FT ³).....	38
pH.....	5
Moisture Content (% BY WEIGHT).....	<3
Particle Count (MM/LB).....	0.3
Attrition (% RESISTANCE).....	85-90

TESTING METHOD

PS 006.01.01 (GSA)
PS 006.01.01 (GSA)
E1521-93 (ASTM)
E727-91 (ASTM)
D2216-80 (ODC)
E1520-93 (ASTM)
P-A 1056 B (GSA)

PRODUCT DESCRIPTION

This coarse sized granule is frequently used as a fertilizer conditioner or drying agent for agricultural grade and turf/ornamental applications. Commonly used as a component in growing media.

MINERAL DESCRIPTION

AGSORB® from Mounds, Illinois is a Montmorillonite mineral in the non-swelling bentonite class. Its low bulk density and high absorptivity allows higher liquid holding capacity. Our mineral processing maximizes the granule's micropore space. AGSORB® heat treatments impart a hard, inert granule with a high resistance to attrition.



MOUNDS, ILLINOIS

TYPICAL CHEMICAL ANALYSIS

Component	Weight % VOLATILE FREE BASIS
SiO ₂	70.8
Al ₂ O ₃	13.4
Fe ₂ O ₃	7.24
MgO.....	2.33
CaO.....	0.65
Na ₂ O.....	0.10
K ₂ O.....	1.52
S.....	0.14
P ₂ O ₅	0.07
MnO.....	0.04
TiO ₂	0.60
BaO.....	0.11

AGSORB®



5/20 LVM ^{red} IL

TYPICAL PRODUCT DATA

Size Guide Number.....	215
Uniformity Index.....	35
Liquid Holding Capacity (% BY WEIGHT).....	30
Bulk Density (LBS/FT ³).....	38
pH.....	5
Moisture Content (% BY WEIGHT).....	<3
Particle Count (MM/LB).....	0.3
Attrition (% RESISTANCE).....	85-90

TESTING METHOD

PS 006.01.01 (GSA)
PS 006.01.01 (GSA)
E1521-93 (ASTM)
E727-91 (ASTM)
D2216-80 (ODC)
E1520-93 (ASTM)
P-A 1056 B (GSA)

PRODUCT DESCRIPTION

This coarse sized granule is frequently used as a fertilizer conditioner or drying agent for agricultural grade and turf/ornamental applications. Commonly used as a component in growing media.

MINERAL DESCRIPTION

AGSORB® from Mounds, Illinois is a Montmorillonite mineral in the non-swelling bentonite class. Its low bulk density and high absorptivity allows higher liquid holding capacity. Our mineral processing maximizes the granule's micropore space. AGSORB® heat treatments impart a hard, inert granule with a high resistance to attrition.

TYPICAL CHEMICAL ANALYSIS

Component	Weight % VOLATILE FREE BASIS
SiO ₂	70.8
Al ₂ O ₃	13.4
Fe ₂ O ₃	7.24
MgO.....	2.33
CaO.....	0.65
Na ₂ O.....	0.10
K ₂ O.....	1.52
S.....	0.14
P ₂ O ₅	0.07
MnO.....	0.04
TiO ₂	0.60
BaO.....	0.11



MOUNDS, ILLINOIS